

# IPOTEC

## *Innovation in Polymer Technology*

Ipotec LLC, 41 Industrial Drive, Exeter, NH 03833, USA  
Tel: (+1) (603) 778 2882 • Fax: (+1) (603) 778 2878 • <http://www.ipotec.com> • e-mail: [info@ipotec.com](mailto:info@ipotec.com)

### **MATERIAL DATA:**

### **PRESSURE SENSITIVE ADHESIVE AA2**

A modified acrylic adhesive system offering good UV light and chemical resistance, together with excellent stability and performance over a wide temperature range. The system is a two-sided tape with a polyester carrier and a red silicone coated polypropylene release liner intended for use as an installation aid. Application surface must be completely clean and dry.

#### **Typical Properties**

Thickness of adhesive and carrier	190 micron (0.0075 inch)
Peel adhesion to steel (PSTC 101 / AFERA 4001)	8.5 N/cm (78 oz/inch)
Continuous service temperature Suitable for short term exposure to	-40°C to 180°C (-40°F to 356°F) 220°C (428°F)
Recommended application temperature	5°C to 60°C (40°F to 140°F)

#### **Shelf Life**

12-18 months when stored in clean, dry conditions at room temperature

Acrylic adhesives are not recommended for use in working environments exposed to moisture.

Unless specifically stated data relates to general-purpose materials. Some properties of special grades may differ. Information provided in this data sheet is indicative and is given in good faith but without warranty, express or implied. Whilst test results are deemed to be reliable, performance of these products is dependent on conditions of use and it is the responsibility of the user to determine suitability for a particular application.